SAFORA

2016-12-07 17:52:03

The bricks are mainly produced from alluvial clays from the sedimentary region of the river Meuse. The river eroded the Ardennes rock formations and carried along the eroded materials. In the flooded region of the river's lower course, these materials were eventually deposited as sediments. Judicious mixing of the clay deposits produces just the right kind of base material for the production of hand form bricks.

COLOUR

red brown with dark shades

	FORMAT		
	HAND FORM		
WF	209 x 101 x 51 mm		
DF	213 x 103 x 66 mm	From one series to another, the average size may slightly differ.	
LF40	245 x 90 x 40 mm		

INDIVIDUAL CHARACTERISTICS

CE

NEN EN 771-1 Cat. I - HD

Norm. compressive strength	>=10 N/mm ²	
Dimensions: tolerance category	T2	
Dimensions: range category	R1	
Dimensional stability	NPD (No performance determined)	
Adhesive strength (mortar)	0,15 N/mm ² (0,30 N/mm ²)	
Active soluble salts	S2	
Reaction to fire	Euroclass A1 (TOC < $0,1\%$)	
Water absorption	<= 15% m/md% (m/md)	
Initial rate of water absorption	>4 kg/m².min ; IW4	
Water vapour diffusion coefficient	5/10 (EN 1745)	
Net dry density	kg/m ³ (D1)	
Gross dry density	1690 kg/m ³ (D1)	
Equivalent thermal conductivity	0,50 W/m.K	
Freeze / thaw resistance	F2	
Dangerous substances	NPD (No performance determined)	
Plante:		

Plants:

Vandersanden Hedikhuizen Bokhovenseweg 8 5256 TC HEDIKHUIZEN (NL) Vandersanden Spijk Spijksedijk 25 6917 AD SPIJK (NL)